

1. Product Description

SN Flux® 607 is a state-of-the-art polycarboxylic ether specifically designed for formulating high-range water-reducing admixtures.

2. Uses

SN Flux® 607 is suitable for formulation of high-range water-reducing / superplasticizing admixtures. **SN Flux® 607** allows formulation of strong water-reducing admixtures to be used especially in concrete designs containing silica fume. **SN Flux® 607** provides high efficiency at low dosage for formulating superplasticizers for self-compacting concrete, precast concrete, and ready-mix concrete applications with high water-reduction capability.

3. Safety

Applicators and supervisors must read the Material Safety Data Sheet (SDS) carefully and follow the instructions provided. Required safety measures must be observed during the application of the material and the applicators must use protective clothing, gloves and goggles. Emptied packages must be handled in compliance with relevant regulations and laws.

4. Storage

Products must be stored between +5 °C and +35 °C in dry, ventilated conditions protected from direct sunlight. Under these conditions, the material will retain its properties in unopened containers for 12 months from the production date. Protect the product from freezing.

Low temperatures may cause crystallization of the product; in this case, the product can be used after heating and homogenizing at +20 °C. The product must be stirred thoroughly before use after prolonged storage.

5. Disclaimer

This document is provided for general information and reflects **Stenkim®**'s laboratory data and field experience at the time of publication. **Stenkim®** reserves the right to revise this information at any time without notice.

Stenkim® warrants that its products conform to the stated specifications on delivery. The buyer is responsible for determining the product's suitability for the intended application and for all conditions of transport, storage, handling, and use. **Stenkim®** accepts no liability for results obtained under conditions outside its control. **Stenkim®**'s liability under this warranty is limited to replacement of non-conforming product and excludes any consequential or indirect damages.

Aqueous Polycarboxylic Ether Solution for Production of Concrete Admixtures

Highlights

- 50% Polycarboxylic ether
- Enhanced water reduction
- High dosage efficiency
- Higher ultimate strength
- Good compatibility with silica fume
- Low air entrainment
- Economical



6. Technical Data

Property	Method	Result
Appearance - Color		Transparent, light yellow
Odor		Characteristic
Chemical Composition		Polycarboxylic ether polymer solution in water
Density	EN ISO 2811-2	1.10 ± 0.01 g/cm ³
pH (23 ± 1 °C)	ISO 4316	4.3 ± 1
Solid Content	EN ISO 3251	50% ± 1%
Viscosity	EN ISO 3219	732 ± 146 cP
Shelf Life		1 year
Packaging		Bulk and 1,100 kg IBCs
Use		High water reduction, Higher ultimate strength, High alkali tolerance

Stenkim[®] reserves the right to make changes to the values in this table at any time.

