

1. Product Description

StenCoat® 2PU EXT is an acrylic-polyurethane based, two-component, decorative top coat. **StenCoat® 2PU EXT** is resistant to chemicals, outside conditions and UV radiation; it does not lose its resistance or its color. It prevents water penetration into the applied surface and increases its resistance to oxidation and abrasion.

It perfectly adheres to concrete and metal surfaces and cures fast.

2. Uses

StenCoat® 2PU EXT can be used on all types of horizontal and vertical concrete and metal surfaces. It is ideal for use on facades. Surfaces coated with **StenCoat® 2PU EXT** are easy to clean and dry quickly.

It prevents dusting on the applied surface. The coating retains its color, elasticity, abrasion resistance, water resistance and UV resistance for a long time.

3. Surface Preparation

Application surfaces must be clean and dry. Application must not be carried out if the surface temperature is below 5 °C or above 40 °C. Epoxy and polyurethane surfaces must be fully cured before the application.

4. Application

It is recommended to condition the materials at 20-30 °C for one day before application. During application, surface and air temperature must be at least 10 °C and the temperature must not drop below 10 °C for 24 hours following the application. Application should not be carried out if there is a possibility of rain.

StenCoat® 2PU EXT is prepared for the application by mixing two components. The components are packaged so that one container of each yields the correct mixing ratio. In cases where one complete package cannot be used, the package must be weighed and proportioned; the mix ratio stated on the package must be observed.

Component B is added into the container of component A and they are mixed for 2-3 minutes at 300-500 rpm without letting air into the mixture. If necessary, it can be thinned by adding up to 20% **StenSolver PU**. Mixed material must be used within the pot life, and thickened material must not be thinned and reused.

StenCoat® 2PU EXT is applied by spraying or by brush and roller. The application is carried out in one or two coats, with 150-350 g per m² per coat.

5. Cleaning

Equipment used can be cleaned at the end of the job with **StenSolver PU**.

6. Safety

Applicators and supervisors must read the Material Safety Data Sheet (SDS) carefully and follow the instructions provided. Emptied packages must be handled in compliance with relevant regulations and laws. The application must be carried out by skilled workers under supervision of experts and the applicators must use all kinds of protective

Two-Component, Exterior Polyurethane Paint

Highlights

- Resistant to outdoor conditions
- Resistant to UV radiation, does not discolor
- Protects the surface against water permeation
- Adheres perfectly to concrete, steel, and many other surfaces
- Easy to apply
- Long pot life
- Fast cure after application
- Catalog colors are available



equipment required for the worksite and the task such as goggles, mask and gloves.

7. Storage

Storage temperature must be between 5 and 30 °C. Packages must not be exposed to direct sunlight. Under these conditions, the material will retain its properties in unopened containers for 12 months from the production date.

Low temperatures may cause crystallization of the product; in this case, the product can be used after heating and homogenizing at +20 °C. The product must be stirred thoroughly before use after prolonged storage.

8. Disclaimer

This document is provided for general information and reflects **Stenkim®**'s laboratory data and field experience at the time of publication. **Stenkim®** reserves the right to revise this information at any time without notice.

Stenkim® warrants that its products conform to the stated specifications on delivery. The buyer is responsible for determining the product's suitability for the intended application and for all conditions of transport, storage, handling, and use. **Stenkim®** accepts no liability for results obtained under conditions outside its control. **Stenkim®**'s liability under this warranty is limited to replacement of non-conforming product and excludes any consequential or indirect damages.

9. Technical Data

Property	Method	Result
Base Polymer		Two-Component Acrylic - Polyurethane
Solid Content		70
Color		Catalog
Density		1.34 ± 0.05 g/cm ³
Density (Dry Film)		1.55 ± 0.05 g/cm ³
Application Thickness (per coat, dry film)		80-200 µm
Abrasion Resistance	ASTM D 4060 CS10/100 rev/1 kg	1 mg
Impact Resistance	ASTM D 2794, 2 kg, 100 cm	No Damage
Radiation Resistance	200 hours, Xenon Arc	No Damage
Pot Life @20 °C		4 hours
Tack-free Time (100 µm) @20 °C		20 minutes
Full Cure Time @20 °C		2 days
Consumption		150-350 g/m ²
Shelf Life		1 year
Packaging		15 kg sets



Stenkim® reserves the right to make changes to the values in this table at any time.

